

PRODUCT DATASHEET

LEXAN™ MARGARD™ HLG 5 Sheet

DESCRIPTION

LEXAN MARGARD HLG5 sheet is a transparent 1-side hard coated UV protected lamination grade offering excellent optical properties for lamination with glass in mainly asymmetrical bullet resistant security glazing panels. It can be specified to match specific levels of threat and has excellent optical clarity. For cleaning instructions consult guidelines. Do not use abrasive or highly alkaline cleaners, never scrape the sheet with squeegees, razor blades or other sharp instruments. Do not clean LEXAN MARGARD HLG5 sheet in hot sun or at elevated temperatures. For removal of paints, marking pen, inks, lipstick, labels, stickers etc. the use of kerosene, naphtha or white spirit is generally effective. Afterwards, a warm final wash should be made, using a mild soap solution and ending with a thorough rinsing with cold water.

TYPICAL PROPERTY VALUES [◆]

Property	Test Method	Units	Value
Physical			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
Mechanical			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
Taber haze - 100 cycles, 500 gram, CS-10F	ASTM D1044	%	1 - 3
Taber haze - 500 cycles, 500 gram, CS-10F	ASTM D1044	%	3 - 8
Thermal			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
Electrical			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
Optical			
Light transmission 2 mm	ASTM D1003	%	92
Light transmission 3 mm	ASTM D1003	%	91
Light transmission 4 mm	ASTM D1003	%	90
Light transmission 5 mm	ASTM D1003	%	90
Light transmission 6 mm	ASTM D1003	%	89
Light transmission 8 mm	ASTM D1003	%	87
Light transmission 9.5 mm	ASTM D1003	%	86
Light transmission 12 mm	ASTM D1003	%	85

◆ Some of the property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.

™ Trademarks of SABIC.

OPTICAL PERFORMANCE

The optical qualities of LEXAN MARGARD HLG5 sheet are the result of constant research in order to help provide high values. This is ensured by in house testing of LEXAN sheets in 3-8 mm thickness according DIN 52305/-A-AZ which specifies optical requirements for glazing in vehicles. During the optical control phase, LEXAN MARGARD HLG5 sheets are examined against a special background, called image magnification, for proper identification of optical imperfections. Our internal manufacturing specifications are under constant supervision of our ISO 9002 approved Quality Management department.

PRODUCT DATASHEET

LEXAN™ MARGARD™ HLG 5 Sheet

PROCESSING

Glass/LEXAN security glazing panels can be produced using different systems for bonding purposes. The autoclaving process is the most common way of laminating glass and LEXAN sheets by means of a polyurethane based interlayer. The differences in thermal behavior between glass and polycarbonate require a sufficient thick interlayer in order to avoid a high stress level. The glass surface needs to be primed for better bond strength with the polyurethane film; contact between primer and LEXAN must be avoided. To avoid air-inclusions, it is recommended to place the construction in a vacuum bag with constantly measured negative pressure of .9 bar during the lamination process. A different way of bonding glass and LEXAN MARGARD HLG5 sheet is to cast a polymer between the different substrates. During the polymerisation process, adhesion takes place between glass and LEXAN sheet.

FIRE TEST PERFORMANCE

LEXAN MARGARD HLG5 sheet has good fire performance against many national fire codes dependent on thickness and color; please check with the local sales office for details.

CHEMICAL RESISTANCE

Although LEXAN MARGARD HLG5 sheet has resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels, we strongly recommend testing in case of applications where the products will come into contact with these or other aggressive chemicals. For symmetrical configurations where both the LEXAN surfaces will be bonded to glass, we advise to apply our non-hard coated product LEXAN Optigard ULG1003.

PRODUCT AVAILABILITY

Product Code : HLG 5 sheet
Standard Size : 2000 x 2920 mm
Thicknesses : 2.5, 3, 4, 5, 6, 8 mm (9.5 and 12mm are optional)
Standard Colors : Clear (112).

For HLG5 different colors and dimensions can be made available by prior arrangements. Such arrangement may affect prices and/or conditions of sale.

RIPPLE ORIENTATION

Ripple direction may play an important role in the optical performance of the sheet. This direction is indicated on the sheet masking. The surface which is foreseen with the -2-strips indicating grade and ripple direction, is hard coated.

FLAT APPLICATIONS ONLY

Due to its mar-resistant coating, LEXAN MARGARD HLG5 sheet cannot be used in curved applications. It is intended for flat applications only.

Americas Headquarters

SABIC Innovative Plastics
 One Plastics Avenue
 Pittsfield, MA 01201
 USA
 T +1-413-448-7125
 Toll-free: 1-800-323-3783
 F +1 (888) 443-2033
 sfsustomerservice@sabic-ip.com

European Headquarters

SABIC Innovative Plastics
 Plasticslaan 1
 4612 PX
 Bergen op Zoom
 The Netherlands
 T +31 164 293684
 F +31 164 293272
 Sfs.info@sabic-ip.com

Pacific Headquarters

SABIC Innovative Plastics
 Specialty Film & Sheet
 1266 Nanjing Road (W)
 16th Floor, Plaza 66
 200040 Shanghai
 China
 T +86 21 62881088 ext. 6733
 F +86 21 6288 0818

E-mail

sfsustomerservice@sabic-ip.com



* Trademark of SABIC Innovative Plastics IP BV

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

™ Trademark of SABIC