

LEXAN™ SG305 OB SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ SG305 OB sheet is an optical bright opal white polycarbonate sheet with unique light diffusing properties while retaining a high light transmission. This both sides UV protected extruded polycarbonate sheet offers significant advantages over many other materials in terms of impact resistance, weathering properties, design freedom and aesthetics. LEXAN SG305 OB sheet is available in an optical bright opal white color with diffusion properties for uniform illumination and has a matt finish on the outside surface for reduced reflection and glare.

LEXAN SG305 OB is an excellent candidate for a variety of industry applications like:

- LED Back lighted signs
- Channel letters
- Lamp diffusers
- Projection screens
- Roller shutters with advertising features

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
IMPACT			
Charpy impact, notched 23°C, 3.0 mm	ISO 179/1eA	kJ/m ²	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	70
THERMAL			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x 10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
ELECTRICAL			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18

PROPERTY	TEST METHOD	UNITS	VALUE
FIRE RATINGS			
Electrical			
Horizontal burn	UL94 HB	-	HB (1.5-6mm)
Glow Wire Flammability Index	IEC-60695-2-12	°C	Pass 850°C (3mm)

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. If minimum certifiable properties are required please contact your local SABIC representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according to ISO 294.

™ Trademarks of SABIC.

OPTICAL PROPERTIES

Gauge / color grade	Light Transmission (%)	Diffusion Factor
2 mm/ WH7C154X	52 ± 4%	0.8
3 mm/ WH7C154X	44 ± 4%	0.8
4 mm/ WH7C154X	37 ± 4%	0.8
5 mm/ WH7C154X	31 ± 4%	0.8
6 mm/ WH7C154X	27 ± 4%	0.8
5 mm/ WH9DO46X	51 ± 4%	0.62

PRODUCT AVAILABILITY

LEXAN™ SG305 OB sheet is available in form of sheets as well as on economical spools, making it easy to cut into desired sizes.

Sheets

Gauge: 2, 3, 4, 5, 6 mm
Size: 2050 x 3050/1250 x 2050

Spools

Gauge: 2+3 mm
 Only available in full web size 2120 mm
 Production: Italy

Standard optical bright white color: WH7C154X

Masking: Top/matte side: co-ex opal white PE with print Bottom side: co-ex transparent PE

LEXAN SG OB sheet is essentially opaque to all wave lengths below 385 nanometers. This useful shielding property prevent discoloration of posters placed behind the LEXAN sheet, second surface graphics and lacquers applied to the reverse side.

UV PROTECTION

LEXAN SG305 OB sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering. The superior UV protected surface treatment is not affected by forming and fabricating and LEXAN SG sheets are therefore backed by a 10 years warranty# against yellowing, loss of light transmission and breakage.

) see warranty for details.

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
 PO Box 5101
 Riyadh 11422
 Saudi Arabia
 T +966 (0) 1 225 8000
 F +966 (0) 1 225 9000
 E info@sabic.com
Email
 sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
 One Plastics Avenue
 Pittsfield, MA 01201
 USA
 Toll-free 1 800 323 3783 ext.3
 T 1 413 448 7125
 F (888) 443 2033
 E sfs.customerservice@sabic-ip.com

Europe

Specialty Film & Sheet
 Plasticslaan 1
 4612 PX
 Bergen op Zoom
 The Netherlands
 T +31 (0)164 293678
 F +31 (0)164 293272
 E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
 2550 Xiupu Road
 Pudong
 201319 Shanghai
 China
 T +86 21 2037 8188
 F +86 21 2037 8288
 E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
 © 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



www.sabic.com/sfs