



Product datasheet

PPS

Physical properties (indicated values)			
PROPERTIES	Test methods	Units	Techtron® HPV PPS
Colour			deep blue
Density	ISO 1183-1	g/cm ³	1.42
Water absorption:			
- after 24/96 h immersion in water of 23 °C (1)	ISO 62	mg	1 / 2
	ISO 62	%	0.01 / 0.02
- at saturation in air of 23 °C / 50 % RH	-	%	0.05
- at saturation in water of 23 °C	-	%	0.20
Thermal Properties			
Melting temperature (DSC, 10 °C/min)	ISO 11357-1/-3	°C	280
Glass transition temperature (DSC, 20 °C/min) - (3)	ISO 11357-1/-2	°C	-
Thermal conductivity at 23 °C	-	W/(K.m)	0.30
Coefficient of linear thermal expansion:			
- average value between 23 and 100 °C	-	m/(m.K)	50 x 10 ⁻⁶
- average value between 23 and 150 °C	-	m/(m.K)	60 x 10 ⁻⁶
- average value above 150 °C	-	m/(m.K)	100 x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	ISO 75-1/-2	°C	115
Max. allowable service temperature in air:			
- for short periods	-	°C	260
- continuously: for min. 20,000 h	-	°C	220
Min. service temperature	-	°C	-20
Flammability:			
- "Oxygen Index"	ISO 4589-1/-2	%	44
- according to UL 94 (1.5 / 3 mm thickness)	-	-	V-0 / V-0
Mechanical Properties at 23 °C			
Tension test:			
- tensile stress at yield / tensile stress at break	ISO 527-1/-2	MPa	NYP / 78
- tensile strength	ISO 527-1/-2	MPa	78
- tensile strain at yield	ISO 527-1/-2	%	NYP
- tensile strain at break	ISO 527-1/-2	%	3.5
- tensile modulus of elasticity	ISO 527-1/-2	MPa	4000
Compression test			
- compressive stress at 1 / 2 / 5 % normal strain	ISO 604	MPa	33 / 65 / 105
Charpy impact strength - unnotched	ISO 179-1 - 1/1eU	kJ/m ²	25
Charpy impact strength - notched	ISO 179 - 1/1eA	kJ/m ²	4
Ball indentation hardness	ISO 2039-1	N/mm ²	160
Rockwell hardness	ISO 2039-2	-	M 82
Electrical Properties at 23 °C			
Electric strength	IEC 60243-1	kV/mm	24
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁴
Surface resistivity	ANSI/ESD STM 11.11	Ohm/sq.	>10 ¹³
Relative permittivity: - at 100 Hz	IEC 60250	-	3.3
- at 1 MHz	IEC 60250	-	3.3
Dielectric dissipation factor tan: - at 100 Hz	IEC 60250	-	0.003
- at 1MHz	IEC 60250	-	0.003
Comparative tracking index (CTI)	IEC 60112	-	100

Note: 1 g/cm³ = 1000 kg/m³; 1 MPa = 1 N/mm²; 1 kVmm = 1 MV/m.

All information is provided after the best of our ability and without liability for essåplast Vink Group. Technical information is largely based on information from our various suppliers of raw materials.